



Institut luxembourgeois de la normalisation  
de l'accréditation, de la sécurité et qualité  
des produits et services

## ILNAS-EN 16128:2015

### **Ophthalmic optics - Reference method for the testing of spectacle frames and sunglasses for nickel release**

Optique ophtalmique - Méthode d'essai  
de référence relative à la libération du  
nickel par les montures de lunettes et les  
lunettes de soleil

Augenoptik - Referenzverfahren für die  
Bestimmung der Nickellässigkeit von  
Brillenfassungen und Sonnenbrillen

11/2015



## National Foreword

This European Standard EN 16128:2015 was adopted as Luxembourgish Standard ILNAS-EN 16128:2015.

Every interested party, which is member of an organization based in Luxembourg, can participate for FREE in the development of Luxembourgish (ILNAS), European (CEN, CENELEC) and International (ISO, IEC) standards:

- Participate in the design of standards
- Foresee future developments
- Participate in technical committee meetings

<https://portail-qualite.public.lu/fr/normes-normalisation/participer-normalisation.html>

### **THIS PUBLICATION IS COPYRIGHT PROTECTED**

Nothing from this publication may be reproduced or utilized in any form or by any mean - electronic, mechanical, photocopying or any other data carries without prior permission!

EUROPEAN STANDARD <sup>ILNAS-EN 16128:2015</sup> **EN 16128**  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

November 2015

ICS 11.040.70

Supersedes CEN/TS 16677:2014, EN 16128:2011

English Version

## Ophthalmic optics - Reference method for the testing of spectacle frames and sunglasses for nickel release

Optique ophtalmique - Méthode d'essai de référence  
relative à la libération du nickel par les montures de  
lunettes et les lunettes de soleil

Augenoptik - Referenzverfahren für die Bestimmung  
der Nickellässigkeit von Brillenfassungen und  
Sonnenbrillen

This European Standard was approved by CEN on 19 September 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
Introduction .....	6
1 Scope .....	7
2 Normative references .....	7
3 Terms and definitions .....	7
4 Principle .....	8
5 Selection of test samples .....	8
6 Simulation of wear and corrosion.....	9
6.1 Preparation of test samples .....	9
6.2 Procedure.....	10
7 Coating test.....	10
7.1 General.....	10
7.2 Apparatus and consumables.....	10
7.3 Preparation of test samples for the coating test.....	11
7.3.1 Parts to be tested.....	11
7.3.2 Dismantling and/or cutting and/or masking .....	11
7.3.3 Determination of test area.....	13
7.3.4 Preparation of electrical contact area .....	13
7.4 Preparation of saline solution.....	13
7.5 Procedure.....	13
7.5.1 Preparation of the electro-chemical cell .....	13
7.5.2 Insertion and connection of the test part in the electro-chemical cell.....	14
7.5.3 Determination of open circuit potential and measurement of electrochemical impedance of test samples.....	14
7.5.4 Calibration and verification of the equipment.....	15
7.6 Calculation of results .....	15
7.6.1 General.....	15
7.6.2 Criteria for pass or fail of the test sample .....	15
7.7 Test report.....	15
8 Release of nickel and its quantitative analytical detection (migration test) .....	16
8.1 General.....	16
8.2 Apparatus and consumables.....	16
8.3 Preparation of test samples for the migration test.....	18
8.3.1 Parts to be tested.....	18
8.3.2 Guidance on selection of test areas on the parts to be tested .....	18
8.3.3 Dismantling and degreasing .....	19
8.4 Procedure.....	19
8.4.1 Preparation of test paper including determination of its area .....	19
8.4.2 Preparation of artificial sweat solution .....	20
8.4.3 Applying artificial sweat solution to the test paper and attaching it to the test sample....	21
8.4.4 Blank sample .....	22
8.4.5 Incubation of test sample with test paper attached (release of nickel into paper) .....	22
8.4.6 Retrieval of the test paper from the test samples .....	22

<b>8.4.7</b>	<b>Analysis of the test papers for nickel .....</b>	<b>22</b>
<b>8.5</b>	<b>Calculation of migration test results .....</b>	<b>24</b>
<b>8.6</b>	<b>Interpretation of migration test results .....</b>	<b>25</b>
<b>8.6.1</b>	<b>General .....</b>	<b>25</b>
<b>8.6.2</b>	<b>Assessment of compliance.....</b>	<b>25</b>
<b>8.7</b>	<b>Test report .....</b>	<b>25</b>
<b>Annex A</b>	<b>(informative) Cutting and masking of test samples (Coating test).....</b>	<b>27</b>
<b>A.1</b>	<b>Fronts.....</b>	<b>27</b>
<b>A.2</b>	<b>Sides (temples) .....</b>	<b>28</b>
<b>Annex B</b>	<b>(normative) Selection of test areas and application of the test paper (Migration test) .....</b>	<b>29</b>
<b>B.1</b>	<b>General .....</b>	<b>29</b>
<b>B.2</b>	<b>Rims .....</b>	<b>29</b>
<b>B.3</b>	<b>Bridge.....</b>	<b>30</b>
<b>B.4</b>	<b>Brace bar .....</b>	<b>31</b>
<b>B.5</b>	<b>Sides.....</b>	<b>32</b>
<b>B.6</b>	<b>Trims .....</b>	<b>34</b>
	<b>Bibliography .....</b>	<b>35</b>

## European foreword

This document (EN 16128:2015) has been prepared by Technical Committee CEN/TC 170 "Ophthalmic optics", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2016, and conflicting national standards shall be withdrawn at the latest by November 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 16128:2011 and CEN/TS 16677:2014.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports the harmonising effect of a restriction adopted under Regulation (EC) No 1907/2006 (REACH) of the European Parliament and the Council.

Compared to EN 16128:2011 and CEN/TS 16677:2014, the following changes have been made:

- a) Compared to EN 16128:2011, the reference test method has been substantially revised:

In the method according to EN 16128:2011 the parts to be tested for nickel release are placed in an artificial sweat test solution for one week. The concentration of dissolved nickel in the solution is determined by atomic absorption spectrometry, inductively-coupled plasma spectrometry or other appropriate analytical method.

The present standard provides, for parts with an organic coating, a coating test based on Electrochemical Impedance Spectroscopy (EIS). The coating test aims at demonstrating that the coating is of sufficient quality to prevent the release of nickel, thereby ensuring that the test sample's nickel release does not exceed the regulatory limit.

For parts without an organic coating, the present standard specifies a migration test. The migration test makes provision for quantitative testing for the amount of nickel released, to determine whether or not the model's nickel release exceeds the regulatory limit. The migration test comprises two steps: Release of nickel by artificial sweat solution into a test paper and the subsequent quantitative analytical detection of the nickel released into the paper.

See also the principle described in Clause 4.

- b) Compared to CEN/TS 16677:2014 the revisions and refinements made are relatively minor, as follows:

For the coating test, see Clause 7:

Amendment of the calculation and presentation of the test result including amendment of the threshold value (see 7.6);

The dummy or test lenses used in the simulation of wear and corrosion are to be kept in the frame.

For the migration test, see Clause 8:

Inclusion of the requirement to prepare and analyze a blank sample with every batch of test samples, along with the relevant specifications of sample preparation and procedure (see 8.4.4);

Specification that the incubation shall be made using a climate chamber; the previously permissible alternative to use an oven with a container for insertion of the test samples has been deleted (see 8.4.5);

Inclusion of more detailed specifications as to the permissible and non-permissible combination of the test papers from the various test areas for the analysis;

Inclusion of directions on how to proceed in the case that the design of a model does not allow the application of the test paper at (one of) the specified location(s);

Amendment of the procedure for the application and sealing of the test paper onto the test area using the sealing film; as an alternative to wrapping with the sealing film it is now also permissible to use a folding technique; see the revised Annex B;

Recommendation that the time between the retrieval of the test papers from the test samples and their extraction and analysis does not exceed 3 d (see 8.4.6).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This document has been prepared under Mandate M/448 issued by the European Commission in the framework of Regulation (EC) No 1907/2006, REACH, in particular Commission Regulation (EC) No 552/2009 of 22 June 2009 amending regulation (EC) No 1907/2006 of the European Parliament and of the Council on the Registration, Evaluation, Authorization and restriction of Chemicals (REACH) as regards Annex XVII RESTRICTIONS ON THE MANUFACTURE, PLACING ON THE MARKET AND USE OF CERTAIN DANGEROUS SUBSTANCES, PREPARATIONS AND ARTICLES.

The aim of the mandate is the revision of the method of analysis to detect the release of nickel from spectacle frames and sunglasses.

The availability of the new reference method for the determination of the release of nickel will provide the reliable framework to enforce the limit value for nickel release of 0,5 µg/cm<sup>2</sup>/week set forth by European Regulation. It will ensure a uniform application and control of the European legislation in all member states.

Harmonizing the test method for nickel release in all member states is vital with a view to protecting effectively the health of the end consumer, that is, the spectacle wearer. Nickel allergy is still the most frequent contact allergy in Europe and a significant health issue.