



Institut luxembourgeois de la normalisation  
de l'accréditation, de la sécurité et qualité  
des produits et services

## ILNAS-EN 1081:2018+A1:2020

### **Resilient, laminate and modular multilayer floor coverings - Determination of the electrical resistance**

Revêtements de sol résilients, stratifiés et  
multicouches modulaires -  
Détermination de la résistance électrique

Elastische, Laminat- und modulare  
mehrschichtige Bodenbeläge -  
Bestimmung des elektrischen  
Widerstandes

09/2020



## National Foreword

This European Standard EN 1081:2018+A1:2020 was adopted as Luxembourgish Standard ILNAS-EN 1081:2018+A1:2020.

Every interested party, which is member of an organization based in Luxembourg, can participate for FREE in the development of Luxembourgish (ILNAS), European (CEN, CENELEC) and International (ISO, IEC) standards:

- Participate in the design of standards
- Foresee future developments
- Participate in technical committee meetings

<https://portail-qualite.public.lu/fr/normes-normalisation/participer-normalisation.html>

### **THIS PUBLICATION IS COPYRIGHT PROTECTED**

Nothing from this publication may be reproduced or utilized in any form or by any mean - electronic, mechanical, photocopying or any other data carries without prior permission!

ILNAS-EN 1081:2018+A1:2020

EUROPEAN STANDARD **EN 1081:2018+A1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2020

ICS 97.150

Supersedes EN 1081:2018

English Version

**Resilient, laminate and modular multilayer floor coverings  
- Determination of the electrical resistance**

Revêtements de sol résilients, stratifiés et  
multicouches modulaires - Détermination de la  
résistance électrique

Elastische, Laminat- und modulare mehrschichtige  
Bodenbeläge - Bestimmung des elektrischen  
Widerstandes

This European Standard was approved by CEN on 1 July 2018 and includes Amendment approved by CEN on 10 August 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## Contents

Page

European foreword .....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions .....	4
4 Sampling.....	5
5 Apparatus and reagents .....	5
6 Method A — For vertical resistance, R1.....	7
7 Method B - For resistance to earth, R2 .....	8
8 Method C for surface resistance, R3 .....	9
9 Calculation and expression of results .....	11
10 Test report.....	11

## European foreword

This document (EN 1081:2018+A1:2020) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2021, and conflicting national standards shall be withdrawn at the latest by March 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 10 August 2020.

This document supersedes A1 EN 1081:2018 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This document specifies test methods for determining:

- a) the vertical resistance,
- b) the resistance to earth,
- c) the surface resistance

of a resilient, laminate and modular multilayer floor covering after installation in test piece or after installation.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 62631-3-1, *Dielectric and resistive properties of solid insulating materials - Part 3-1: Determination of resistive properties (DC methods) - Volume resistance and volume resistivity - General method (IEC 62631-3-1)*

ISO 48, *Rubber, vulcanized or thermoplastic - Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **vertical resistance R1**

electrical resistance measured between a tripod electrode on the surface of a test piece and an electrode attached to the underside of the test piece

Note 1 to entry: See Figure 1 for tripod electrode and see Figure 2 for testing of vertical resistance.

### 3.2

#### **resistance to earth R2**

electrical resistance measured between a loaded tripod electrode on the surface of a laid floor covering and earth

### 3.3

#### **surface resistance R3**

electrical resistance measured between two tripod electrodes set up at a fixed distance of 100 mm apart on a laid floor covering

Note 1 to entry: See Figure 4 for the electrical resistance measured between two tripod electrodes and see Figure 3 for distance of 100 mm apart on a laid floor covering.

## 4 Sampling

For method A or when measurements are done in laboratory, take a representative sample from the whole of the available material. In the case of rolls, take approximately a third of the test pieces from the area close to the edges, the distance between the outer edge of the sample and the nearest edge of the roll being between 50 mm and 100 mm.

## 5 Apparatus and reagents

### 5.1 Tripod electrode

The tripod electrode (Figure 1) shall be capable of comprising a triangular aluminium plate with an insulating layer on the upper surface and three cylindrical feet of conductive rubber on the underside at a distance of 180 mm apart.

The rubber feet shall have a hardness in accordance with ISO 48 of 50 IRHD to 70 IRHD, and the electrical resistance of each rubber foot shall be less than  $10^3$  Ohm when tested between two metal surfaces.

NOTE A “soft electrode” such as that described above is able to provide a more intimate contact with a smooth floor covering and in practice this type of electrode has been found to be the most satisfactory.

### 5.2 Load

The load (F) shall be capable of exerting a minimum force of 300 N on the tripod electrode.

This can be achieved by using a person's body weight. In method C, one person may stand with a foot on each electrode.

### 5.3 Power supply

The power supply shall fulfil the requirements given in EN 62631-3-1.

### 5.4 Resistance meter

**[A1]** The resistance meter shall fulfil the requirements given in EN 62631-3-1. It shall be calibrated to determine the resistance  $R$  of a floor covering to an accuracy of  $\pm 5\%$  in the range  $10^3$  Ohm to  $10^{11}$  Ohm and an accuracy of  $\pm 10\%$  for greater than  $10^{11}$  Ohm. The tolerances for the open circuit voltage shall be:

- 10 V  $\pm$  0,5 V for resistance below  $1,0 \times 10^6 \Omega$
- 100 V  $\pm$  5 V for resistance between  $1,0 \times 10^6 \Omega$  and  $1,0 \times 10^{11} \Omega$
- 500 V  $\pm$  25 V for resistance above  $1,0 \times 10^{11} \Omega$

When implementing tests according to procedures 6.5, 7.4 and 8.4, start with the voltage set to 10 V, if the value exceeds  $10^6 \Omega$ , select 100 V and repeat the measurement. If the value for this second measurement exceeds  $10^{11} \Omega$ , select 500 V and make a final measurement. Record the reading which matches the voltage and resistance range specified above, if either of the following situations occur:

- a) the measured resistance at 10 V is greater than  $1,0 \times 10^6 \Omega$  and the measured resistance at 100 V is less than  $1,0 \times 10^6 \Omega$ ; or