

May 2022

ICS 91.100.01

Will supersede CEN/TS 17195:2018

English Version

Construction products: Assessment of release of dangerous substances - Analysis of inorganic substances in eluates

Produits de construction - Évaluation du relargage de
substances dangereuses - Analyse des substances
inorganiques dans les éluats

Bauprodukte: Bewertung der Freisetzung von
gefährlichen Stoffen - Analyse von anorganischen
Stoffen in Eluaten

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 351.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| Contents | | Page |
|--|---|------|
| European foreword | | 3 |
| Introduction | | 4 |
| 1 | Scope | 5 |
| 2 | Normative references | 5 |
| 3 | Terms and definitions | 6 |
| 4 | Abbreviations | 8 |
| 5 | Sample pre-treatment | 8 |
| 6 | Selection of suitable analytical test method | 9 |
| 6.1 | Table of test methods | 9 |
| 6.2 | General validation information | 9 |
| 7 | Method performance | 11 |
| 8 | Expression of results | 11 |
| 9 | Test report | 11 |
| 10 | Test performance | 12 |
| Annex A (informative) Precision data for analysis of inorganic substances in eluates from construction products | | 13 |
| Bibliography | | 27 |

European foreword

This document (prEN 17195:2022) has been prepared by Technical Committee CEN/TC 351 “Construction products - Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

This document is currently submitted to the CEN Enquiry.

This document will supersede CEN/TS 17195:2018.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

Introduction

Following an extended evaluation of available methods for content analysis in construction products (CEN/TR 16045, [1]) it was concluded that eluate analysis methods are very similar to analytical methods used to determine content after digestion of a solid matrix.

This document has been adopted from the work carried out in the context of CEN/TC 292 and is very similar to EN 16192 [2].

This document is part of a modular horizontal approach which was adopted in CEN/TC 351. “Horizontal” means that the methods can be used for a wide range of materials and products with certain properties. “Modular” means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole chain of measurement (from sampling to analyses). Beneficial features of this approach are that modules can be replaced by better ones without jeopardizing the standard chain and duplication of work of in different Technical Committees for Products can be avoided as far as possible.

The modules that relate to the standards developed in CEN/TC 351 are specified in CEN/TR 16220 [3], which distinguishes between the modules. This document belongs to the analytical step.

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain construction product to determine certain characteristics, it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

1 Scope

This document specifies analytical methods for the determination of major, minor and trace elements and of anions in aqueous eluates from construction products. It refers to the following 67 elements:

Aluminium (Al), antimony (Sb), arsenic (As), barium (Ba), beryllium (Be), bismuth (Bi), boron (B), cadmium (Cd), calcium (Ca), cerium (Ce), caesium (Cs), chromium (Cr), cobalt (Co), copper (Cu), dysprosium (Dy), erbium (Er), europium (Eu), gadolinium (Gd), gallium (Ga), germanium (Ge), gold (Au), hafnium (Hf), holmium (Ho), indium (In), iridium (Ir), iron (Fe), lanthanum (La), lead (Pb), lithium (Li), lutetium (Lu), magnesium (Mg), manganese (Mn), mercury (Hg), molybdenum (Mo), neodymium (Nd), nickel (Ni), palladium (Pd), phosphorus (P), platinum (Pt), potassium (K), praseodymium (Pr), rubidium (Rb), rhenium (Re), rhodium (Rh), ruthenium (Ru), samarium (Sm), scandium (Sc), selenium (Se), silicon (Si), silver (Ag), sodium (Na), strontium (Sr), sulphur (S), tellurium (Te), terbium (Tb), thallium (Tl), thorium (Th), thulium (Tm), tin (Sn), titanium (Ti), tungsten (W), uranium (U), vanadium (V), ytterbium (Yb), yttrium (Y), zinc (Zn), and zirconium (Zr) and to the following four anions: Cl⁻, Br⁻, F⁻, SO₄²⁻.

This document also describes how to measure general parameters like pH, electrical conductivity, DOC/TOC.

The methods in this document are applicable to construction products.

NOTE Construction products include e.g. mineral-based products (S); bituminous products (B); metals (M); wood-based products (W); plastics and rubbers (P); sealants and adhesives (A); paints and coatings (C), see also CEN/TR 16045.

The selection of analytical methods to be applied is based on the required sensitivity of the method, which is provided for all substance - analytical procedure combinations.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1484, *Water analysis — Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)*

EN 16687:2015, *Construction products — Assessment of release of dangerous substances — Terminology*

prEN 17197, *Construction products: Assessment of release of dangerous substances — Analysis of inorganic substances in digests and eluates — Analysis by inductively coupled plasma optical emission spectrometry (ICP-OES)*

prEN 17200, *Construction products: Assessment of release of dangerous substances — Analysis of inorganic substances in digests and eluates — Analysis by inductively coupled plasma mass spectrometry (ICP-MS)*

EN 27888, *Water quality — Determination of electrical conductivity (ISO 7888)*

EN ISO 5667-3, *Water quality — Sampling — Part 3: Preservation and handling of water samples (ISO 5667-3)*

EN ISO 10304-1, *Water quality — Determination of dissolved anions by liquid chromatography of ions — Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate (ISO 10304-1)*

EN ISO 10523, *Water quality — Determination of pH (ISO 10523)*

EN ISO 12846, *Water quality — Determination of mercury — Method using atomic absorption spectrometry (AAS) with and without enrichment (ISO 12846)*

EN ISO 15586, *Water quality — Determination of trace elements using atomic absorption spectrometry with graphite furnace (ISO 15586)*

EN ISO 17852, *Water quality — Determination of mercury — Method using atomic fluorescence spectrometry (ISO 17852)*

ISO 10359-1, *Water quality — Determination of fluoride — Part 1: Electrochemical probe method for potable and lightly polluted water*

ISO 17378-1, *Water quality — Determination of arsenic and antimony — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO 17378-2, *Water quality — Determination of arsenic and antimony — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

ISO/TS 17379-1, *Water quality — Determination of selenium — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO/TS 17379-2, *Water quality — Determination of selenium — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 16687:2015 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 eluate

solution obtained from a leaching test

[SOURCE: EN 16687:2015, 4.2.7]

3.2 leachant

liquid that is brought into contact with the test portion in the leaching procedure

Note 1 to entry: Usually demineralized water is used as leachant for laboratory leaching tests.

[SOURCE: EN 16687:2015, 4.2.6]

3.3 leaching test

laboratory test for the determination of the release of substances from a construction product into a leachant