

# ILNAS

Institut luxembourgeois de la normalisation  
de l'accréditation, de la sécurité et qualité  
des produits et services

## ILNAS-EN 14188-2:2004

### **Joint fillers and sealants - Part 2: Specifications for cold applied sealants**

Produits d'obturation et de scellement  
de joints - Partie 2 : Spécifications pour  
produits de scellement appliqués à froid

Fugeneinlagen und Fugenmassen - Teil 2:  
Anforderungen an kalt verarbeitbare  
Fugenmassen

12/2004



## National Foreword

This European Standard EN 14188-2:2004 was adopted as Luxembourgish Standard ILNAS-EN 14188-2:2004.

Every interested party, which is member of an organization based in Luxembourg, can participate for FREE in the development of Luxembourgish (ILNAS), European (CEN, CENELEC) and International (ISO, IEC) standards:

- Participate in the design of standards
- Foresee future developments
- Participate in technical committee meetings

<https://portail-qualite.public.lu/fr/normes-normalisation/participer-normalisation.html>

### **THIS PUBLICATION IS COPYRIGHT PROTECTED**

Nothing from this publication may be reproduced or utilized in any form or by any mean - electronic, mechanical, photocopying or any other data carries without prior permission!

EUROPEAN STANDARD <sup>ILNAS-EN 14188-2:2004</sup> **EN 14188-2**  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

December 2004

ICS 93.080.20

English version

**Joint fillers and sealants - Part 2: Specifications for cold applied sealants**

Produits d'obturation et de scellement de joints - Partie 2 :  
Spécifications pour produits de scellement appliqués à froid

Fugeneinlagen und Fugenmassen - Teil 2: Anforderungen  
an kalt verarbeitbare Fugenmassen

This European Standard was approved by CEN on 4 November 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

# Contents

	<b>Page</b>
Foreword.....	3
<b>1 Scope .....</b>	<b>4</b>
<b>2 Normative references .....</b>	<b>4</b>
<b>3 Terms and definitions .....</b>	<b>5</b>
<b>4 Classification and specification .....</b>	<b>5</b>
<b>5 Requirements .....</b>	<b>6</b>
<b>6 Evaluation of conformity.....</b>	<b>10</b>
<b>7 Marking, labelling and packaging .....</b>	<b>11</b>
<b>Annex A (normative) Initial Type Testing and frequencies of testing for Factory Production Control .....</b>	<b>13</b>
<b>Annex B (informative) Example of a product data sheet.....</b>	<b>14</b>
<b>Annex C (informative) Processing information for installation of cold applied joint sealants .....</b>	<b>16</b>
<b>Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives .....</b>	<b>17</b>
<b>Bibliography .....</b>	<b>21</b>

ILNAS-EN 14188-2:2004 - Preview only Copy via ILNAS e-Shop

## Foreword

This document (EN 14188-2:2004) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

This document is one of a series of standards as listed below.

EN 14188-1, *Joint fillers and sealants — Part 1: Specifications for hot applied sealants.*

EN 14188-2, *Joint fillers and sealants — Part 2: Specifications for cold applied sealants.*

prEN 14188-3, *Joint fillers and sealants — Part 3: Specifications for preformed joint seals.*

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This document specifies the requirements for cold applied normal and fuel resistant joint sealants for concrete pavements to be used in roads, parking decks, bridge decks, airfields and other trafficked areas.

This document does not cover the use in gasoline stations, jet fuel stations on airfields and the chemical industry.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14187-1, *Cold applied joint sealants — Part 1: Test method for the determination of rate of cure.*

EN 14187-2, *Cold applied joint sealants — Part 2: Test method for the determination of tack free time.*

EN 14187-3, *Cold applied joint sealants — Part 3: Test method for the determination of self-levelling properties.*

EN 14187-4, *Cold applied joint sealants — Part 4: Test method for the determination of the change in mass and volume after immersion in test fuels.*

EN 14187-5, *Cold applied joint sealants — Part 5: Test method for the determination of the resistance to hydrolysis.*

EN 14187-6, *Cold applied joint sealants — Part 6: Test method for the determination of the adhesion/cohesion properties after immersion in chemicals liquids.*

EN 14187-7, *Cold applied joint sealants — Part 7: Test method for the determination of the resistance to flame.*

EN 14187-8, *Cold applied joint sealants — Part 8: Test method for the determination of the artificial weathering by UV-irradiation.*

prEN 14187-9, *Cold applied joint sealants — Test methods — Part 9: Function testing of joint sealants.*

EN 26927:1990, *Building construction - Jointing products - Sealants - Vocabulary (ISO 6927:1981).*

EN 28340:1990, *Building construction - Jointing products - Sealants - Determination of tensile properties at maintained extension (ISO 8340:1984).*

EN 28394, *Building construction - Jointing products - Determination of extrudability of one-component sealants (ISO 8394:1988).*

EN 29048, *Building construction — Jointing products — Determination of extrudability of sealants using standardized apparatus (ISO 9048:1987).*

EN ISO 7389, *Building construction - Jointing products - Determination of elastic recovery of sealants (ISO 7389:2002).*

EN ISO 7390:2003, *Building construction - Jointing products - Determination of resistance to flow of sealants (ISO 7390:2003).*

EN ISO 9001, *Quality management systems — Requirements (ISO 9001:2000).*

EN ISO 9047, *Building construction — Jointing products — Determination of adhesion/cohesion properties of sealants at variable temperatures (ISO 9047:2001)*.

EN ISO 10563, *Building construction — Sealants for joints — Determination of change in mass and volume (ISO 10563:1991)*.

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 26927:1990 and the following apply.

#### 3.1

##### **manufacturer's limiting value MLV**

manufacturer's stated minimum or maximum value to be met during testing according to the requirements of this document

#### 3.2

##### **manufacturer's declared value MDV**

value declared by the manufacturer accompanied by a declared tolerance

#### 3.3

##### **cold climate area**

areas in which the temperature can go below  $-25\text{ }^{\circ}\text{C}$  and the opening of the joint can exceed 35 %

### 4 Classification and specification

#### 4.1 Cold applied sealant

According to the field of their application, cold applied joint sealants for joints in concrete pavements have to fulfil different requirements.

Depending on their chemical base and their compositions sealants are available as single or multi-component systems. To make identification easy they shall be designated by the following symbols:

**Table 1 — Systems of cold applied joint sealants**

Material	System
Single component system	S
Multi components system	M

**Table 2 — Types of cold applied joint sealants**

Material	Type
Self levelling type	sl
Non sag type	ns