

---

# INTERNATIONAL STANDARD



# 2006

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION · МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ · ORGANISATION INTERNATIONALE DE NORMALISATION

---

## Synthetic rubber latex – Determination of high-speed mechanical stability

*Latex d'élastomère de synthèse – Détermination de la stabilité mécanique à vitesse élevée*

First edition – 1974-05-15

ISO 2006:1974 - Preview only Copy via ILNAS e-Shop

---

UDC 678.031 : 678.7 : 620.173

Ref. No. ISO 2006-1974 (E)

**Descriptors** : elastomers, synthetic elastomers, latex, tests, physical tests, stability.

ISO 2006-1974 (E)

Price based on 2 pages

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

Prior to 1972, the results of the work of the Technical Committees were published as ISO Recommendations; these documents are now in the process of being transformed into International Standards. As part of this process, International Standard ISO 2006 replaces ISO Recommendation R 2006-1971 drawn up by Technical Committee ISO/TC 45, *Rubber and rubber products*.

The Member Bodies of the following countries approved the Recommendation :

Australia	Greece	Spain
Austria	Hungary	Sweden
Canada	India	Switzerland
Ceylon	Israel	Turkey
Egypt, Arab Rep. of	Italy	United Kingdom
France	New Zealand	U.S.A.
Germany	South Africa, Rep. of	U.S.S.R.

No Member Body expressed disapproval of the Recommendation.

# Synthetic rubber latex – Determination of high-speed mechanical stability

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method for the determination of the high-speed mechanical stability of synthetic rubber latex.

The stirring disk which is specified has a greater diameter than that specified for natural rubber latex in ISO 35, *Natural rubber latex – Determination of mechanical stability*.

The test is applicable to synthetic rubber latices which have a viscosity, determined with the L instrument in accordance with ISO 1652, of up to 200 mPa·s (200 cP). Latices of higher viscosity shall be tested after dilution to a viscosity of 200 mPa·s (200 cP) or less, provided that such dilution<sup>1)</sup> does not reduce the concentration of the latex by more than 10 % total solids.

The duration of stirring shall be so selected that the latex does not increase in temperature to more than 60 °C and does not exceed a height of 100 mm in the latex container. The duration of stirring shall be agreed between the interested parties and shall not be longer than 30 min or less than 1 min. In the case of a latex which contains ammonia, the duration of stirring shall be limited, since loss of ammonia by evaporation during the test may cause additional destabilization.

The test does not necessarily indicate the stability of a synthetic rubber latex to high shear stress, for which a rubbing test may be more applicable.

## 2 REFERENCES

ISO 123, *Rubber latex – Sampling*.

ISO 124, *Rubber latices – Determination of total solids content*.

ISO 1652, *Rubber latex – Determination of viscosity*.

## 3 PRINCIPLE

Stirring of the latex at high speed.

The amount of coagulum formed is regarded as an inverse measure of the mechanical stability of the latex.

## 4 REAGENT

**Soap solution**, 5 % solution of potassium oleate of pH value 10, or, for use with a latex which is coagulated by potassium oleate solution, 5 % solution of a synthetic anionic surfactant.

Distilled water or water of equivalent purity shall be used wherever water is specified.

## 5 APPARATUS

**5.1 Mechanical stability measuring apparatus<sup>2)</sup>**, consisting of the following items :

**5.1.1 Latex container**, flat-bottomed, cylindrical, at least 100 mm high, with an internal diameter of  $58 \pm 2$  mm. The inner surface shall be smooth, and a glass container is preferred.

**5.1.2 Stirring apparatus**, consisting of a vertical stainless steel shaft of sufficient length to reach to the bottom of the latex container (5.1.1) and tapering to 6,35 mm diameter at its lower end, where is attached a horizontal, smooth, stainless steel disk  $36,12 \pm 0,03$  mm in diameter and  $1,58 \pm 0,05$  mm thick by means of a threaded stud at the exact centre of the disk. The apparatus shall maintain a stirring speed of  $14\,000 \pm 200$  rev/min throughout the test, at which speed the shaft shall not run out of true by more than 0,25 mm.

**5.1.3 Holder** for the latex container (5.1.1). The holding arrangement shall ensure that the axis of the rotating shaft is concentric with that of the latex container and that the bottom of the stirring disk is  $13 \pm 2$  mm from the inner surface of the bottom of the latex container.

**5.2 Preliminary filter** of stainless steel wire cloth with an average aperture width of  $180 \pm 15$   $\mu$ m.

**5.3 Test filter** consisting of a disk of stainless steel wire cloth with an average aperture width of  $180 \pm 15$   $\mu$ m, dried to constant mass and weighed to the nearest 1 mg, firmly clamped between two stainless steel rings of equal internal diameter between 25 and 50 mm.

1) Dilution of the latex decreases its stability because the balance of free and absorbed soap is changed.

2) Suitable instruments are commercially available.